

RECEIVED
CENTRAL FAX CENTER
DEC 20 2006

IN THE CLAIMS

Complete listing of the claims:

1-8. (Cancelled)

9. (Withdrawn) A transparent conductive film comprising the transparent resin film of claim 1, wherein a moisture proof layer containing a metal oxide, a metal nitride or a metal carbide is provided on one side of the transparent resin film and a transparent conductive layer is provided on the moisture proof layer or on the other side of the transparent resin film.

10. (Withdrawn) The transparent conductive film of claim 9, wherein the transparent conductive layer is provided on the moisture proof layer and on the other side of the transparent resin film.

11. (Withdrawn) The transparent conductive film of claim 9, wherein the moisture proof layer is comprised mainly of silicon oxide.

12. (Withdrawn) The transparent conductive film of claim 10, wherein the moisture proof layer is comprised mainly of silicon oxide.

13. (Withdrawn) The transparent conductive film of claim 9, wherein the moisture proof layer is amorphous.

14. (Withdrawn) The transparent conductive film of claim 9, wherein the moisture proof layer or the transparent conductive layer is formed by inducing electric discharge between two opposed electrodes at atmospheric pressure or at approximately atmospheric pressure by applying high frequency voltage across the two opposed electrodes to excite a reactive gas between the two opposed electrodes to a plasma state, and the exposing the transparent resin film to the reactive gas of the plasma state.

Case No. KOT-0088
Serial No. 10/762,173

2

15. (Withdrawn) The transparent conductive film of claim 14, wherein a frequency of the high frequency voltage is from 100 kHz to 150 MHz, and an output power supplied is from 1 to 50 W/cm².

16. (Withdrawn) A liquid crystal display comprising, as a substrate, the transparent conductive film of claim 9.

17. (Withdrawn) An organic EL display comprising, as a substrate, the transparent conductive film of claim 9.

18. (Withdrawn) A touch panel comprising, as a substrate, the transparent conductive film of claim 9.

19. (Currently amended) A method of manufacturing ~~the a~~ transparent resin film of claim 1 according to a solution cast method, the method comprising the steps of:


dissolving an alkoxysilane in a first solvent containing an alcohol having 1 to 4 carbon atoms to obtain an alkoxysilane polycondensation product solution;

dissolving cellulose ester in a second mixture solvent of methylene chloride and ethyl alcohol having a methylene chloride to ethyl alcohol ration of from 95:5 to 80:20 to obtain a cellulose ester solution;

mixing the alkosysilane polycondenssation product solution anf the cellusloe ester solution to provide a cellulose ester dope containing the alcohol in an amount of 1 to 40% by weight; and

casting the resulting cellulose ester dope on a support, wherein the alkoxysilane is represented by the following formula 1:

Formula 1



Case No. KOT-0088
Serial No. 10/762,173

3

wherein R and R' independently represent a hydrogen atom or a substituent; and n represents an integer of 3 or 4.

20. (New) The method of Claim 19, wherein a degree of substitution of the cellulose ester satisfies the following mathematical expressions 1 and 2:


Expression 1: $0 < Y < 1.5$.

Expression 2: $1.0 < X+Y \leq 2.9$.

wherein X represents a degree of substitution of an acetyl group and Y represents a degree of substitution of a substituent having an alkoxysilyl group.

21. (New) The method of Claim 19, wherein the content of the polycondensation product is less than 20% by weight based on the transparent film and wherein the polycondensation product is represented by the following formula 2:

Formula 2



wherein R represents a hydrogen atom or a substituent; and n represents an integer of 3 or 4.

22. (New) The method of Claim 19, wherein the transparent film contains a plasticizer in an amount less than 1% by weight.

23. (New) The method of Claim 19, wherein the ratio $R_0(480)/R(590)$ obtained by dividing retardation in plane $R_0(480)$ of the film at a wavelength 480 nm by retardation in plane $R(590)$ of the film at a wavelength 590 nm is from 0.8 to less than 1.0.

24. (New) The method of claim 19, wherein the transparent film contains the cellulose ester in an amount of not less than 80% by weight and the alkoxysilane polycondensation product in an amount of 1 to less than 20% by weight in terms of silicon dioxide.

25. (New) The method of Claim 19, wherein the first solvent contains methylene chloride.

26. (New) The method of Claim 19, wherein the first solvent contains methyl acetate.

Case No. KOT-0088
Serial No. 10/762,173

5